## **IN THE CLAIMS**:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Claims 3-5 and 7 have been amended and claims 8-14 have been added as follows:

## **Listing of Claims:**

Claim 1 (original): An agglomerate comprising fine primary particles of an inorganic compound except for silica, the agglomerate satisfying the following expressions (a) to (e):

(a) 
$$0.5 \le dp_{50} \le 20 \ [\mu m]$$

(b) 
$$0 \le \alpha \le 2.5$$
 [-]

(c) 
$$30 \le Sw$$
 [m<sup>2</sup>/g]

(d) 
$$20 \le St \le 150$$
 [MPa] and

(e) 
$$200 \le Sta \le 600[MPa]$$
,

wherein

 $dp_{50}$ : the average particle diameter [ $\mu m$ ] of the agglomerate measured by Microtrac-FRA, a laser analysis type particle size distribution measurement apparatus,

 $\alpha$ : the value calculated by dividing the difference between the particle diameter  $d_{90}$  of cumulative 90% minus sieve particles of the agglomerate and the particle diameter  $d_{10}$  of cumulative 10% minus sieve particles of the agglomerate calculated by the Microtrac-FRA, a laser analysis type particle size distribution measurement

Seiya SHIMIZU, et al.

(§371 of International Application PCT/JP03/13127)

apparatus by the average particle diameter dp<sub>50</sub> according to the following equation:

$$\alpha = (d_{90} - d_{10})/dp_{50}$$

d<sub>90</sub>: the particle diameter of cumulative 90% minus sieve particles of the agglomerate measured by the Microtrac-FRA, a laser analysis type particle size distribution measurement apparatus,

d<sub>10</sub>: the particle diameter of cumulative 10% minus sieve particles of the agglomerate measured by the Microtrac-FRA, a laser analysis type particle size distribution measurement apparatus,

Sw: the BET specific surface area of the agglomerate [m<sup>2</sup>/g],

St: the tensile strength [MPa] required to break the agglomerate with the particle diameter  $4\mu$  m, measured by a micro compression testing machine manufactured by Shimadzu Corporation, and

Sta: the tensile strength [MPa] required to break 30% of the particle diameter of the agglomerate with the particle diameter  $4\mu$  m, measured by a micro compression testing machine manufactured by Shimadzu Corporation.

Claim 2 (original): The agglomerate according to claim 1, wherein the agglomerate satisfies the solidified apparent density satisfies the following expression (f):

(f) 
$$0.2 \le \rho bp \le 0.8 [g/cm^3]$$
,

wherein

Seiya SHIMIZU, et al.

(§371 of International Application PCT/JP03/13127)

pbp: the solidified apparent density [g/cm<sup>3</sup>] of the agglomerate powder measured by a powder tester manufactured by Hosokawa Micron Co., Ltd..

Claim 3 (currently amended): The agglomerate according to claim 1 [[or 2]], wherein the agglomerate is surface-treated with at least one kind selected from aliphatic acids, alicyclic carboxylic acids, aromatic carboxylic acids, their sulfonic acids and resin acids, their metal salts, ammonium salts, amine salts, esters; aliphatic, alicyclic, and aromatic sulfonic acids; coupling agents; silicone oils; paraffin; copolymers of  $\alpha,\beta$ -monoethylenically unsaturated carboxylic acids and monomers copolymerizable with  $\alpha,\beta$ -monoethylenically unsaturated carboxylic acids, their metal salts ammonium salts, amine salts, esters; phosphoric acid esters; and industrial soaps.

Claim 4 (currently amended): The agglomerate according to any one of claims 1 to 3 claim 1, wherein the agglomerate comprises calcium carbonate.

Claim 5 (currently amended): A resin composition containing a resin mixed with the agglomerate according to any one of claims 1 to 4 claim 1.

Claim 6 (original): The resin composition according to claim 5, wherein the resin is selected from polyolefin resins, polyester resins, polyamide resins, polyvinyl chloride resins, and biodegradable resins.

Claim 7 (currently amended): The resin composition according to claim 5 [[or 6]], wherein the resin composition is in the form of a film, a sheet or a fiber.

Claim 8 (new): The agglomerate according to claim 2, wherein the agglomerate is surface-treated with at least one kind selected from aliphatic acids, alicyclic carboxylic acids, aromatic carboxylic acids, their sulfonic acids and resin acids, their metal salts, ammonium salts, amine salts, esters; aliphatic, alicyclic, and aromatic sulfonic acids; coupling agents; silicone oils; paraffin; copolymers of  $\alpha,\beta$ -monoethylenically unsaturated carboxylic acids and monomers copolymerizable with  $\alpha,\beta$ -monoethylenically unsaturated carboxylic acids, their metal salts ammonium salts, amine salts, esters; phosphoric acid esters; and industrial soaps.

Claim 9 (new): The agglomerate according to claim 2, wherein the agglomerate comprises calcium carbonate.

Claim 10 (new): The agglomerate according to claim 3, wherein the agglomerate comprises calcium carbonate.

Claim 11 (new): A resin composition containing a resin mixed with the agglomerate according to claim 2.

## Seiya SHIMIZU, et al. (§371 of International Application PCT/JP03/13127)

Claim 12 (new): A resin composition containing a resin mixed with the agglomerate according to claim 3.

Claim 13 (new): The resin composition according to claim 11, wherein the resin is selected from polyolefin resins, polyester resins, polyamide resins, polyvinyl chloride resins, and biodegradable resins.

Claim 14 (new): The resin composition according to claim 12, wherein the resin is selected from polyolefin resins, polyester resins, polyamide resins, polyvinyl chloride resins, and biodegradable resins.